



MasterFormat: 07 91 23



NO. 791

DECEMBER 2014
(Supersedes January 2011)

KOOL-ROD™

Backer Rod for Cold-Applied Sealants

DESCRIPTION

KOOL-ROD is a closed cell, polyethylene, flexible, rope-like foam joint backing material.

This material is virtually non-absorbent and chemically inert to most solvents. KOOL-ROD will not stain or adhere to sealant materials. It is fully compatible with acrylic, butyl, polyurethane, polysulfide, silicone, and most other cold-applied sealant compounds.

KOOL-ROD is specifically designed as a compressible backing material to be used in conjunction with a wide variety of cold-applied joint sealants.

USES

KOOL-ROD is highly adaptable for both vertical and horizontal applications. It is commonly used in glazing operations, copings, between precast panels, and around door and window perimeters. It provides the perfect backing for all types of construction, expansion, isolation, control, and pavement joints.

FEATURES/BENEFITS

- Controls depth of sealant/Ensures proper joint design ratio.
- Forces sealant against joint sidewalls/Provides maximum sidewall adhesion.
- Sealants will not adhere to KOOL-ROD/Eliminates three-sided joint adhesion failure.
- Closed-cell foam technology/Does not allow air or moisture entrapment.
- Easily compressible, lightweight/Installs quickly, stays in place.
- Easy to handle, smaller packaging/Added contractor convenience.

PACKAGING

Diameter	Joint Width	Footage/Carton	Packaging
1/4" (6 mm)	3/16" (4 mm)	6400 LF (1950 m)	2 spools/carton
3/8" (9.5 mm)	1/4" (6 mm)	3600 LF (1097 m)	2 spool/carton
1/2" (12 mm)	3/8" (9 mm)	2500 LF (762 m)	1 spools/carton
5/8" (15 mm)	1/2" (12 mm)	1550 LF (472 m)	1 spool/carton
3/4" (19 mm)	5/8" (15 mm)	1100 LF (335 m)	1 spools/carton
7/8" (22 mm)	11/16" (18 mm)	850 LF (259 m)	1 spool/carton
1" (25 mm)	3/4" (19 mm)	550 LF (168 m)	1 spool/carton
1 1/4" (31 mm)	7/8" (22 mm)	400 LF (122 m)	1 spool/carton

Color: Dark Gray

SPECIFICATIONS

- ASTM C 1330-96, Type C
- ASTM D 5249-92, Type 3

APPLICATION

Joint or opening must be clean, dry, and free of obstructions. Select the proper rod diameter and cut to length or use directly from the spool. With a blunt instrument or roller, uniformly install rod at a level recommended by the sealant manufacturer, specifier, or architect. Generally, the depth of the joint after KOOL-ROD is installed should be half the width. Very large and very small joints vary in terms of this depth-to-width ratio.

CONTINUED ON REVERSE

Do not tear, puncture, twist, or overly compress the backer rod during installation. Caution should be used to avoid any situation where voids may form and trap air/moisture between backer rod and sealant. Care should also be taken to prevent the introduction of air bubbles into the sealant during mixing (if any) and/or installation.

LEED INFORMATION

May help contribute to LEED credits:

- MR Credit 2: Construction Waste Management
- MR Credit 4: Recycled Content
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.